

Date: Jan. 27, 06

CHEMICAL RESISTANCES

ZX611A57 POLYESTER 'Z' GREY

ZX611H25 POLYESTER 'Z' BEIGE

TEST MEDIUM	TIME	RESULT
Ketchup	4 weeks	No change
Mustard	4 weeks	No change
Pickles	4 weeks	No change
Beer	4 weeks	No change
Brandy	4 weeks	No change
Acetic Acid	4 weeks	No change
Seawater	4 weeks	No change

N.B. The information on this sheet is based on experience or tests in the laboratory and is published in good faith. We can accept no responsibility for loss or damage, which may result from accident, or misuse for operations not under our direct control.