1 May 2008

TEST REPORT for: Automatic Coating
211 Nugget Ave.
Toronto, Ontario
M1S 3B1

for: Craft-Bilt Materials Ltd.
Markham, Ontario

PRODUCTS TESTED: ZX611W25 SUPERDURABLE SANDTEX DECK WHITE
ZX611A68 SUPERDURABLE SANDTEX DECK LIGHT GRAY

TEST RESULTS: RESISTANCE TO CLEANING REAGENTS

- CLR
- Fantastic
- Varsol

Description of the test:

- Coatings sprayed on Q-panels at 4-6 mils
- Baking schedule: 7 minutes @400°F(204°C)

The panels were immersed in the cleaning reagents for 24 hours at room temperature. After 24 hours, the panels were rinsed with warm water and allowed to dry at room temperature.

No color change, no softening, no blistering, no loss of adhesion, no embrittlement nor any effect observed.

The cleaning reagents have no effect on the coatings.

Mila S. Martin

Toronto Laboratory
Protech Chemicals Ltd.